

Anti-aging Pearl Pressed Eye Shadow - "Green"

Ref: CC0199

Color Cosmetics

Product Name	INCI Name	%WW	Supplier
A		100.00	
Silk Mica	Mica	13.30	www.vwr.com
Softouch CCS 102	Boron Nitride	2.50	www.advceramiccos.com
Kemilub EZ-V	Zinc Stearate	7.00	www.undesa.com
Talc Powder	Talc	23.50	www.riedelhaen.com
Prestige® Bright Mystic Green	Mica (and) Titanium Dioxide	20.00	www.sudarshan.com
Prestige® Emerald	Mica (and) Titanium Dioxide (and) Iron Oxides (and) Ferric Ferrocyanide	20.00	www.sudarshan.com
B			
Dow Corning 200 Fluid 5CST	Dimethicone	5.00	www.dowcorning.com
	Cyclomethicone (and)		
Dow Corning 9040 Elastomer Blend	Dimethicone Crosspolymer	5.00	www.dowcorning.com
Sexy Silk	Fragrance	0.70	www.drom.de
MPC-Milk Peptid Complex (16.7% aqueous solution)	Whey Protein	3.00	www.clr-berlin.com

Procedure

1. Mix phase A
2. Add phase B to phase A and stir until homogenous
3. Press eye shadow at 150 bar for 30 s

Stability

Stable for at least 6 months at RT and 40°C.

Sudarshan Chemical Industries Ltd.

Global Head Office:
162 Wellesley Road, Pune
411001, India
Tel : +91 20 260 58 888
Fax : +91 20 260 58 222
e-mail : cosmeticpigments@sudarshan.com

Sudarshan Europe BV

Crystal tower, 24th floor, Orlyplein 10,
PO Box 58176, 1040 HD, Amsterdam,
The Netherlands
Tel: +31 (0)20 475 2311
Fax: +31 (0)20 475 2312
e-mail: eu@sudarshan.com

Sudarshan North America Inc.

76 N. Walnut street,
Ridgewood NJ,
USA 07450.
Tel: +1 201 882 2135
Fax: +1 201 882 0157
e-mail: usa@sudarshan.com