

Brightened Beauty - "Pressed Powder"

Ref: CC0672

Color Cosmetics

| Product Name | INCI Name | %WW | Supplier |
|-----------------------------|---------------------------------------|-------|--|
| A | | | |
| Talc Powder | Talc | 50.65 | www.vwr.com |
| Azco Mica BC 120 WG | Mica | 20.00 | www.akzonobel.com |
| Zinc Stearate | Zinc Stearate | 2.00 | www.vwr.com |
| Orgasol 2002D/Nat | Nylon 12 | 3.50 | www.atofinchemicals.com |
| Rokonsal SSH-1 | Methylparaben, Propylparaben | 0.30 | www.biochema.de |
| Prestige® Super Soft Bronze | Mica (and) Iron Oxides | 3.00 | www.sudarshan.com |
| Prestige® Super Soft Silver | Mica (and) Titanium Dioxide | 9.00 | www.sudarshan.com |
| B | | | |
| Myritol 312 | Caprylic/ Capric Triglyceride | 4.00 | www.cognis.com |
| Wacker Belsil CM 1000 | Cyclopentasiloxane, Dimethiconol | 4.00 | www.wacker.com |
| Imwitor 380 | Glyceryl Cocoate/ Citrate/ Lactate | 1.00 | www.sasolwax.com |
| Water | Aqua | 2.00 | - |
| dl-alpha-Tocopheryl Acetate | Tocopheryl Acetate | 0.50 | www.jandekker.com |
| Pink Velvet DF | Fragrance | 0.05 | www.bell-europe.com |

Procedure

1. Weigh in phase A and mix with speedmixer (30s/2000rpm)
2. Add phase B to phase A and mix again with speedmixer (30s/2500rpm) until homogeneous
3. Press powder at 150 bar for 30 s

Sudarshan Chemical Industries Ltd.

Global Head Office:
162 Wellesley Road, Pune
411001, India
Tel : +91 20 260 58 888
Fax : +91 20 260 58 222
e-mail : cosmeticpigments@sudarshan.com

Sudarshan Europe BV

Crystal tower,24th floor, Orlyplein 10,
PO Box 58176, 1040 HD, Amsterdam,
The Netherlands
Tel: +31 (0)20 475 2311
Fax: +31 (0)20 475 2312
e-mail: eu@sudarshan.com

Sudarshan North America Inc.

76 N. Walnut street,
Ridgewood NJ,
USA 07450.
Tel: +1 201 882 2135
Fax: +1 201 882 0157
e-mail: usa@sudarshan.com