


Pigments

Pigments for
Coatings



SUDARSHAN
Outshine. Outdo.

Pigments

For Coatings

Product Name & Code	C. I. Name	Decorative Paints		Industrial Coatings					Light fastness Full Tone/Tint	Weather fastness Full Tone/Tint	Heat Stability (°C)	Overspray
		Solvent Base	Water Base	Automotive OEM	Automotive Refinish	Industrial Paints	Powder Coatings	Coil Coatings				
Sudaperm™ Yellow 3032C	PY 138	●	●	○	○	●	●		8/7	5/4	200	5
Sudaperm™ Yellow 3030C	PY 138	●	●	○	○	●	●		8/7	5/4	200	5
Sudaperm™ Yellow 2903	PY 151	●		○	●	●	●		8/7	5/4	180	5
Sudaperm™ Yellow 2906	PY 154	●	●	○	●	●	●		8/7	5/4	160	5
Sudacolor™ Yellow G	PY 1	●	●						7/5	—	—	—
Sudafast™ Yellow 130C	PY 74	●	●			○			7/5	4/2	—	—
Sudafast™ Yellow 127	PY 74	●	●			○			7/5	4/2	—	—
Sudafast™ Yellow 117	PY 74	●	●						7/5	4/2	—	—
Sudafast™ Yellow 128C	PY 74		●						6/5	4/2	—	—
Sudacolor™ Yellow 118	PY 65	●	●						6/5	4/2	—	3
Sudacolor™ Yellow 119C	PY 65	●	●						6/5	4/2	—	3
Sudafast™ Yellow 134	PY 83	●	●			●	●		7/6	4/3	200	4-5
Sudafast™ Yellow 137C	PY 83	●	○			●	●		7/5	—	200	—
Sudaperm™ Yellow 2938C	PY 139	●		○	●	●	●		8/7	4-5/3-4	200	5
Sudaperm™ Yellow 2937C	PY 139	●		○	●	●	●		8/7	4-5/3-4	200	5
Sudaperm™ Yellow 2935	PY 139	●		○	●	●	●		7-8/7	4/3-4	200	5
Sudaperm™ Yellow 2929C	PY 110	○	●	●	●	●	●	○	8/7	5/4	200	5
Sudaperm™ Yellow 2925C	PY 110	○	○	●	●	●	●	○	8/7	5/4	200	4-5
Sudaperm™ Orange 2919	PO 64						●	○	5-6/3	—	180	—
Sudaperm™ Orange 2915C	PO 36	●	●	○	●	●	●		8/7	5/4	160	5
Sudacolor™ Red 401	PR 4	●	●						6/3	—	—	—
Sudacolor™ Red 417	PR 3	●	●						6/4	—	—	—
Sudacolor™ Red 415	PR 3	●	○						6/4	—	—	—
Sudafast™ Red 341	PR 112	●	●						7-8/4-5	—	—	—
Sudafast™ Red 336	PR 112	●	●						7/6	—	—	—
Sudafast™ Red 331	PR 112	●	●						7/5-6	—	—	—
Sudaperm™ Red 2963C	PR 170	●	●		●	●	●		7/5	4/2	180	4-5
Sudaperm™ Red 2967C	PR 170	●	●		●	●	●		7/5	4/2	180	4-5
Sudaperm™ Red 2951C	PR 264		○	●	●	●	●	○	8/8	5/5	200	5
Sudaperm™ Red 2953C	PR 264			●	●	●	●	○	8/7	5/4	200	4-5
Sudaperm™ Red 2987	PV 19	●	●	○	●	●	●	●	8/7	5/4	200	5
Sudaperm™ Red 2988C	PV 19	●	●	●	●	●	●	●	8/7	5/4	200	5
Sudaperm™ Pink 2998	PR 122	●	●						8/7	5/4	200	5
Sudaperm™ Pink 3000C	PR 122	●	●	●	●	●	●	●	8/7	5/4	200	5
Sudaperm™ Red Violet 2995	PV 19	●	●	●	●	●	●	●	8/7	5/4	200	5
Sudaperm™ Violet 2940C	PV 23	●	●	○	●	●	●	●	8/8	5/4	180	5
Sudaperm™ Violet 2941C	PV 23	●	●	○	●	●	●	●	8/8	5/4	180	5
Sudafast™ Blue 2662	PB 15:1	●	●	○	●	●	○	●	8/8	5/5	200	5

Note: Light fastness is assessed on 1-8 Blue Wool Scale where 1= Poor & 8 = Excellent
Weather fastness is assessed on 1-5 Grey Scale where 1= Poor & 5= Excellent


● Suitable for application ○ Potential Use

Pigments

For Coatings

Product Name & Code	C. I. Name	Decorative Paints		Industrial Coatings					Light fastness Full Tone/Tint	Weather fastness Full Tone/Tint	Heat Stability (°C)	Overspray	
		Solvent Base	Water Base	Automotive OEM	Automotive Refinish	Industrial Paints	Powder Coatings	Coil Coatings					
Sudafast™ Blue 2764	PB 15:1							●		8/8	5/5	200	5
Sudafast™ Blue 2773	PB 15:2	○	●	●	●	●	●	●	●	8/8	5/5	200	5
Sudafast™ Blue 2778C	PB 15:3	●	●			○	○	○		8/8	5/5	200	5
Sudafast™ Blue 2784	PB 15:3	●	●		○	●	○	●		8/8	5/5	200	5
Sudafast™ Blue 2785	PB 15:3	●	●							8/8	5/5	200	5
Sudafast™ Blue 2789	PB 15:3						●			8/8	5/5	200	5
Sudafast™ Blue 2796	PB 15:4	●	●	●	●	●	○	●		8/8	5/5	200	5
Sudafast™ Green 2727C	PG 7	●	●	○	●	●	●	●		8/8	5/5	200	5
Sudafast™ Green 2729C	PG 7	●	●	○	●	●	●	●		8/8	5/5	200	5

● Suitable for application ○ Potential Use




Sudaperm™
Yellow 3032C PY138

Sudaperm™
Yellow 3030C PY138

Sudaperm™
Yellow 2903 PY151

Sudaperm™
Yellow 2906 PY154

Sudacolor™
Yellow G PY1



Sudafast™
Yellow 130C PY74

Sudafast™
Yellow 127 PY74

Sudafast™
Yellow 117 PY74

Sudafast™
Yellow 128C PY74

Sudacolor™
Yellow 118 PY65




Sudacolor™
Yellow 119C PY65

Sudafast™
Yellow 134 PY83

Sudafast™
Yellow 137C PY83

Sudaperm™
Yellow 2938C PY139

Sudaperm™
Yellow 2937C PY139



Sudaperm™
Yellow 2935 PY139

Sudaperm™
Yellow 2929C PY110


Sudaperm™
Yellow 2925C PY110

Sudaperm™
Orange 2919 P064

Sudaperm™
Orange 2915C P036

Pigments

For Coatings



Sudacolor™
Red 401 PR4

Sudacolor™
Red 417 PR3

Sudacolor™
Red 415 PR3

Sudafast™
Red 341 PR112

Sudafast™
Red 336 PR112




Sudafast™
Red 331 PR112

Sudaperm™
Red 2963C PR170

Sudaperm™
Red 2967C PR170

Sudaperm™
Red 2951C PR264

Sudaperm™
Red 2953C PR264



Sudaperm™
Red 2987 PV19

Sudaperm™
Red 2988C PV19

Sudaperm™
Pink 2998 PR122

Sudaperm™
Pink 3000C PR122

Sudaperm™
Red Violet 2995 PV19



Sudaperm™
Violet 2940C PV23

Sudaperm™
Violet 2941C PV23

Sudafast™
Blue 2662 PB15:1

Sudafast™
Blue 2764 PB15:1

Sudafast™
Blue 2773 PB15:2




Sudafast™
Blue 2778C PB15:3

Sudafast™
Blue 2784 PB15:3

Sudafast™
Blue 2785 PB15:3

Sudafast™
Blue 2789 PB15:3

Sudafast™
Blue 2796 PB15:4



Sudafast™
Green 2727C PG7

Sudafast™
Green 2729C PG7

Color Reproduction: For technical reasons connected with color reproduction, the colors shown may not exactly match the pigment colors and do not represent a particular finish.

Tint shades are reproduced with a ratio of Pigment: TiO₂ = 1:10.

Disclaimer: The information included here is based on the most reliable data generated by our laboratories. Since the performance of a pigment also depends on the additives and polymers used, we recommend that customers should test the suitability of the pigment for their end application. However, if we are provided with testing methods and samples, we would be glad to do the same. We will do our best to provide products of consistent quality, within the scope of the general conditions of sale and delivery. Should, in spite of these precautions, any liability be established, the damage, if any will be limited to the value of the goods delivered by us and used by you.

Why Us?



About Us

Sudarshan is a leading global producer of performance colorants, manufacturing an extensive range of Organic, Inorganic and Pearlescent pigments as well as Dispersions.

Sudarshan's quality pigments and dispersions add outstanding performance, long term protection, brilliant color and special effect to the Coatings, Plastics, Printing Ink, Cosmetics, Paper and Textile industries.

Sudarshan has over 60 years of manufacturing experience, with sales in more than 85 countries and sales presence in North America, Europe, China and Latin America.

Technical Capability, Infrastructure and Commitment to Quality

Our commitment to being a world class solution provider is maintained by our technical capabilities and an infrastructure that supports the wide customer base that we cater to.

This capability is a combination of a comprehensive gate-review process in product development; state-of-the-art analytical testing facilities that enable a wide range of investigative methods and a data driven approach; and an application lab that accurately recreates the behavior of our product in our customer's application to provide the optimal solution.

Each year, we invest substantially in R&D and Applications Service to support our customers technically and to extend our range of products to meet our customers' requirements.

Our quality, environment and safety systems are based on and accredited with international standards. Our improvement programs are being driven through 6-sigma methodology.



Ecological & Toxicological Association
of Dyes & Organic pigment manufacturers



ISO 9001:2015

ISO 45001:2018

ISO 14001:2015

ISO 17025:2017

Pigments

Contact Us

Sudarshan Chemical Industries Limited

Registered Office:
Eleven West Panchshil, 7th Floor, Survey No. 25,
Near PAN Card Club Road, Baner, Pune - 411 069, India.
Tel: +91 20 682 81 200
Email: contact@sudarshan.com

Sudarshan Europe B.V.

Kingsfordweg 151
1043 GR Amsterdam
Tel: +31 (0)20 491 9417
Email: eu@sudarshan.com

Sudarshan North America Inc.

76 N. Walnut Street
Ridgewood, NJ
USA 07450
Tel: +1 201 652 2046
Email: ordersusa@sudarshan.com

Sudarshan Japan Limited


8F KS Building 4-5-20 Kojimachi
Chiyoda-ku, Tokyo, Japan - 102 - 0083
Tel: +81 3 6867 1484
Email: japan@sudarshan.com

Sudarshan Mexico S. de R.L. de CV.

Av. Chalma s/n Oficina b-13
Jardines de la Hacienda Sur, 54720
Cuautitlan Izcalli, Edo. de Mexico, Mexico
Tel: +52 55 2472 0246
Email: mexico@sudarshan.com

Sudarshan (Shanghai) Trading Company Limited

Room 1911, 19/F New Hualian Mansion,
East Wing, No. 755 Middle Huaihai Road,
Huangpu District, Shanghai, China, 200020
Tel: +86 21 2215 7500, +86 21 2215 7559
Email: china@sudarshan.com



Ecological and Toxicological
Association of Dyes and
Organic Pigments Manufacturers

www.sudarshan.com