

## Sudacolor™ Yellow 197D

### Pigment for Inks

#### Product Description

Sudacolor Yellow 197D is a transparent Disazo pigment with high color depth and reddish tone. It is a suitable product for making NC pigment concentrates.

#### Product Information

|                               |                   |                            |               |
|-------------------------------|-------------------|----------------------------|---------------|
| <b>Chemical Type</b>          | Disazo            | <b>CAS NO.</b>             | 5102-83-0     |
| <b>C. I. Name</b>             | Pigment Yellow 13 | <b>EINECS / ELINCS NO.</b> | 225-822-9     |
| <b>C. I. Constitution No.</b> | 21100             | <b>Physical Appearance</b> | Yellow powder |

#### Application Profile

|                      |    |                |    |
|----------------------|----|----------------|----|
| Sheetfed Ink         | -- | Vinyl Ink      | -- |
| Silkscreen Ink       | -- | Water Base Ink | -- |
| Metal Decorative Ink | -- | CLPP Base Ink  | -- |
| Polyamide Base Ink   | -- | PU Ink         | -- |
| NCPU Ink             | ●  | NCPA Ink       | -- |

● Recommend | ○ Potential Use | -- Not recommended

#### Technical Performance

| Heat Stability | Soap Fastness |                    | Full Shade | Tint |
|----------------|---------------|--------------------|------------|------|
| 180°C          | 4-5           | Weather Resistance | -          | -    |
|                |               | Light Fastness     | 4          | 3    |

#### Physical Properties

|                      |            |   |     |
|----------------------|------------|---|-----|
| Oil Absorption       | 37 ± 10%   | Bleeding in Xylene                        | 2-3 |
| Specific Gravity     | 1.25 ± 0.1 | Bleeding in Methyl Ethyl Ketone           | 2-3 |
| Bulk Density (g/ml)  | 0.67 ± 0.1 | Bleeding in Ethyl Acetate                 | 3   |
| pH Value             | 4 - 7      | Bleeding in Cellosolve                    | 3   |
| Volatile Matter      | 1% max     | Bleeding in Mineral Turpentine            | 3   |
| Resistance to Acid   | 5          | Specific Surface Area (m <sup>2</sup> /g) | -   |
| Resistance to Alkali | 4          | Average size of Primary Particle (nm)     | -   |

- ✓ **Light fastness:** Light fastness rating is assessed on 1 to 8 Blue Wool scale where 1 = 'Poor' and 8 = 'Excellent'.
- ✓ **Weather fastness:** Weather fastness rating is assessed on 1 to 5 Grey scale where 1 = 'Poor' and 5 = 'Excellent'.
- ✓ **Heat stability:** Heat stability values given indicate the maximum temperature at which the pigments can be stored for 10 min. in the full shade and in reductions without undergoing any significant change in shade.
- ✓ **Soap Fastness:** The Soap Fastness is assessed on 1 to 5 Grey scale where 1 = 'Poor' and 5 = 'Excellent'.
- ✓ **Oil absorption:** The oil absorption is determined on the basis of EN ISO 787-5 and given in g linseed oil per 100 gm. pigment.
- ✓ **Solvent bleeding:** The bleeding in solvents is tested using the powder grades and the visual rating given on 1 to 5 Grey scale where 1 = 'Heavy bleeding' and 5 = 'No bleeding'

#### Disclaimer –

The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.