

in Styrene acrylic resin

Other solvent based coatings

Sudarshan formulation No. 02238

Rev. Number: 01.01

04/02

Function	Product	Producer	PBW
Styrene acrylic resin	Pliolite® AC4	Synthomer	8.60
Styrene acrylic resin	Pliolite® AC80	Synthomer	7.90
Polyester solid modified	TEGO® AddBond LTH	Evonik	1.20
Plasticizer	RESAMIN® HF 480	Allnex	1.50
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPO	Sudarshan	23.60
Magnesium silicate	Microtalc™ IT Extra	Elementis	5.90
Titanium dioxide	TIOXIDE® TR92	Venator	7.10
Grind.			
Solvent	White Spirit (100-160 °C)		27.70
Solvent	Solvesso™ 100	ExxonMobil	16.50
Add while stirring.			

100.00

Gf-OS11_002-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.