

in Water soluble alkyd

Other water based coatings

Sudarshan formulation No. 06277

Rev. Number: 01.01

06/06

Function	Product	Producer	PBW
Short oil alkyd	WorléeSol 65 A,70%BG/BuOH/PnB 1:1:1	Worlée-Chemie	12.50
Neutralizing agent	Ammonia, 25%		0.70
Water soluble after neutralization with ammonia, 25%.			
	Demi. water		20.00
Coalescing agent	DOWANOL™ PnB	Dow	1.20
Add while stirring.			
Anticorrosive pigment	Calcium Phosphate CP	Sudarshan	6.00
Corrosion inhibitor	Loxanol® MI 6627	BASF	1.80
Calcium carbonate	Millicarb®	Omya	8.25
Magnesium silicate	Micro Talc ST20	Imerys	4.05
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	7.20
Dispersing agent	Hydropalat® 535 N	BASF	0.50
Drier	SOLAPLEX® WEB Cobalt 8%	Venator	0.25
Drier	Nuodex® WEB Manganese 9	Venator	0.20
Grind 20 minutes with a bead mill.			
	Demi. water		8.10
Add while stirring.			
Short oil alkyd	WorléeSol 65 A,70%BG/BuOH/PnB 1:1:1	Worlée-Chemie	13.60
Neutralizing agent	Ammonia, 25%		0.60
Water soluble after neutralization with ammonia, 25%.			
	Demi. water		14.95
Premix and add to the grind.			
Antiskinning agent	Exkin® 2	Venator	0.10
Add while stirring.			
			100.00
Adjust pH 8.2 - 8.5 with ammonia, 25%.			
Specifications			
PVC in %			34.2

Gf-OW08_006-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.