

in Long oil alkyd

Solvent based coatings

Sudarshan formulation No. 98141

Rev. Number: 01.01

08/98

Function	Product	Producer	PBW
Long oil alkyd	ETERKYD 1106-M-70-3	Eternal Materials	40.00
Rheology modifier	BENTONE® SD-3	Elementis	0.30
Solvent	White Spirit		8.40
Drier	Octa-Soligen® Calcium 10, basic	Borchers	0.30
Anticorrosive pigment	HEUCOPHOS® ZPO	Sudarshan	9.00
Barium sulfate	Albasoft 70	Sachtleben Minerals	24.00
Magnesium silicate	FINNTALC M10	Elementis	10.00
Titanium dioxide	KRONOS® 2190	KRONOS	5.30
Grind.			
Drier	Octa-Soligen® 173	Borchers	2.40
Antiskinning agent	Borchi® Nox M2	Borchers	0.30
Add components separately while stirring.			

100.00

Specifications	
Vol.-% Anticorrosive pigment reg. pigment/filler	18.7
Solids in %	78.0

Gf-SB02_001-01_01C

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.