

## in High solid alkyd

Solvent based coatings

Sudarshan formulation No. 527-04

Rev. Number: 01.01

02/10

Function	Product	Producer	PBW
Short oil alkyd	WorléeKyd TT 3502	Worlée-Chemie	26.95
Wetting and dispersing agent	SOYA-LECITHIN-CONCENTRATE™ STA	Lubrizol	0.30
Rheology modifier	BENTONE® SD-2	Elementis	0.20
Rheology modifier	AEROSIL® 200	Evonik	0.30
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Sudarshan	7.55
Titanium dioxide	KRONOS® 2190	KRONOS	6.30
Iron and manganese oxide black	BAYFERROX® 303 T	LANXESS	0.40
Magnesium silicate	FINNTALC M15	Elementis	8.50
Mica/quartz/chlorite filler	Plastorit® Micro	Imerys	8.50
Calcium/Magnesium carbonate	MICRODOL® 1	Omya	19.10
Grind 40 minutes at 4000 rpm with a bead mill.			
Glycol ether	Solvenon® PM	BASF	2.00
Solvent	Methoxypropyl acetate		4.10
Solvent	Xylene		14.90
Drier	Octa-Soligen® Calcium 10, basic	Borchers	0.40
Drier	Octa-Soligen® 69 HS	Borchers	0.20
Antiskinning agent	Borchi® Nox M2	Borchers	0.30
Add components separately while stirring.			
			100.00

## Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	12.3
PVC in %	47.3
PVC / CPVC	0.8
Solids in %	71.9

Gf-SB03\_005-01\_01C

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.