

## in Silicone resin

Solvent based coatings

Evonik Tego formulation No. 3002

Rev. Number: 01.01

08/07

Function	Product	Producer	PBW
Silicone epoxy hybrid resin	SILIKOPON® EW	Evonik	26.30
Copper chromite black spinel	HEUCODUR® Black 9-100	Sudarshan	10.40
Mica/quartz/chlorite filler	Plastorit® 0000	Imerys	10.20
Magnesium silicate	Microtalc™ IT Extra	Elementis	4.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Sudarshan	5.00
Solvent	Solvesso™ 100	ExxonMobil	13.00
Rheology modifier	AEROSIL® R 972	Evonik	0.90
Solvent	Methoxypropyl acetate		3.80
<b>Grind.</b>			
Silicone epoxy hybrid resin	SILIKOPON® EW	Evonik	15.80
Solvent	Butyl acetate		4.60
Solvent	Xylene		6.00
<b>Add while stirring.</b>			

---



---

100.00

Gf-SB10\_007-01\_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.