

## in Coil coating

Specialty coatings

Evonik formulation No. Wa 3401

Rev. Number: 01.01

11/95

Function	Product	Producer	PBW
Polyester resin	DYNAPOL® LH 833-03	Evonik	40.00
Anticorrosive pigment	HEUCOPHOS® SAPP	Sudarshan	7.40
Titanium dioxide	KRONOS® 2059	KRONOS	10.20
Rheology modifier	AEROSIL® 200	Evonik	0.40
Solvent	Solvesso™ 150	ExxonMobil	9.00
<b>Grind with a bead mill.</b>			
Polyester resin	DYNAPOL® LH 833-03	Evonik	8.00
Blocked aliphatic polyisocyanate	Desmodur® BL 3175 SN	Covestro	5.60
Melamine resin	CYMEL® 325 resin	Allnex	3.60
Epoxy resin	EPON™ Resin 1004F	Hexion	5.60
Catalyst	Dabco® T-12	Evonik	0.20
Solvent	Methoxypropyl acetate		3.00
Solvent	Solvesso™ 100	ExxonMobil	7.00
<b>Add while stirring.</b>			
			100.00
<b>Specifications</b>			
Solids in %			52.0

Gf-SC01\_003-01\_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.