

## in Aircraft primer

Specialty coatings

Sudarshan formulation No. 410-12

Rev. Number: 01.01

10/07

Function	Product	Producer	PBW
<b>Component A</b>			
Epoxy resin	Araldite® GT 6071	Huntsman Advanced Materials	18.30
Solvent	Xylene		9.60
Emulsifier	Soya lecithin		0.30
Coalescing agent	DOWANOL™ PMA	Dow	3.20
<b>Premix.</b>			
Anticorrosive pigment	HEUCOPHOS® SRPP	Sudarshan	13.20
Corrosion inhibitor	HEUCORIN® RZ	Sudarshan	1.50
Magnesium silicate	Microtalc™ IT Extra	Elementis	7.60
Iron oxide yellow pigment	BAYFERROX® 3920	LANXESS	4.50
Titanium dioxide	KRONOS® 2190	KRONOS	3.40
Barium sulfate	Albasoft 70	Sachtleben Minerals	4.90
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	0.10
Rheology modifier	BENTONE® SD-1	Elementis	0.60
<b>Grind with a bead mill.</b>			
Epoxy resin	Araldite® GT 6071	Huntsman Advanced Materials	9.10
Coalescing agent	DOWANOL™ PMA	Dow	4.50
<b>Add while stirring.</b>			
			80.80
<b>Component B</b>			
Curing agent	Aradur® 3776 XW 55	Huntsman Advanced Materials	10.95
Solvent	n-Butyl alcohol		1.20
Solvent	1-Propanol		1.35
Solvent	Solvesso™ 100	ExxonMobil	2.85
Coalescing agent	DOWANOL™ PM	Dow	2.85
<b>Premix and add while stirring.</b>			
			19.20
<b>Mix components A and B thoroughly prior to use.</b>			
			100.00
<b>Specifications</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			47.0
PVC in %			36.0
CPVC in %			45.0
PVC / CPVC			0.8

Gf-SC02\_004-01\_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.