

in Shop primer

Specialty coatings

Sudarshan formulation No. 06275

Rev. Number: 01.01

06/06

Function	Product	Producer	PBW
Polyvinyl butyral (PVB)	MOWITAL® B 30 HH	Kuraray	11.00
Solvent	Butyl alcohol		14.00
Solvent	Xylene		17.00
Solvent	Isopropyl alcohol		20.00
Mix until uniform solution prior to addition.			
Epoxy resin	BECKOPOX® EP 301/75X	Allnex	5.30
Coalescing agent	DOWANOL™ PM	Dow	2.70
Titanium dioxide	KRONOS® 2190	KRONOS	21.00
Mix until uniform paste prior to addition.			
Solvent	Xylene		4.25
Rheology modifier	HDK® H15	Wacker Chemie	0.50
Wetting and antissettling agent	ADDITOL® XL 270	Allnex	0.25
Mix until uniform paste prior to addition.			
Anticorrosive pigment	Calcium Phosphate CP	Sudarshan	4.00
Grind.			
			100.00
Specifications			
Vol.-% Anticorrosive pigment reg. pigment/filler			22.0

Gf-SC03_006-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.