

in Wash primer

Specialty coatings

Sudarshan formulation No. 746-07

Rev. Number: 01.01

04/15

Function	Product	Producer	PBW
Polyvinyl butyral (PVB)	MOWITAL® BA 20 S	Kuraray	10.80
Solvent	n-Butyl alcohol		60.70
Solvent	Xylene		22.10
Mix until uniform solution prior to addition.			
Anticorrosive pigment	HEUCOPHOS® CMP	Sudarshan	4.60
Magnesium silicate	FINNTALC M15	Elementis	1.40
Rheology modifier	AEROSIL® R 972	Evonik	0.40
Grind with a bead mill.			

100.00

Specifications	
Vol.-% Anticorrosive pigment reg. pigment/filler	70.0
PVC in %	19.4
PVC / CPVC	0.4
Solids in %	17.2

Gf-SC03_013-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.