

in Direct to metal

Specialty coatings

Sudarshan formulation No. 954-03

Rev. Number: 01.02

09/23

Function	Product	Producer	PBW
	Demi. water		8.20
Rheology modifier	ACRYSOL™ RM-5000	Dow	0.50
Wetting and dispersing agent	TEGO® Dispers 750 W	Evonik	0.40
Substrate wetting agent	SURFYNOL® 104 E	Evonik	0.40
Defoamer	BYK®-023	BYK-Chemie	0.20
Neutralizing agent	AMP-90™	ANGUS Chemie	0.20
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Sudarshan	2.40
Titanium dioxide	TIOXIDE® TR92	Venator	12.10
Grind with a bead mill.			
	Demi. water		1.60
Defoamer	BYK®-024	BYK-Chemie	0.15
Styrene acrylic dispersion	Pliotec® HDT12	Synthomer	65.10
Solvent	Mono propylene glycol		1.00
Glycol ether	DOWANOL™ DPM	Dow	0.80
Glycol ether	DOWANOL™ DPnB	Dow	1.20
Coalescing agent	Eastman Optifilm™ Enhancer 300	Eastman Chemical	0.50
Rheology modifier	ACRYSOL™ RM-8W	Dow	0.20
Flash rust inhibitor	HEUCOFLASH™ LQ2	Sudarshan	0.45
	Demi. water		4.60
Add while stirring.			

100.00

Adjust pH 8.5 with ammonia, 25%.

Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	20.0
PVC in %	11.2
PVC / CPVC	0.2
Solids in %	47.1

Gf-SC04_018-01_02A

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.