

## in UV cured system

Specialty coatings

Sudarshan formulation No. 12361 in acc. to Bayer form. No. FWO 4037-1

Rev. Number: 01.01

08/10

Function	Product	Producer	PBW
Urethane acrylate	DESMOLUX® XP 2666	Allnex	49.15
Adhesion promoter	EBECRYL® 168	Allnex	4.10
Acrylic resin	Photomer® 4039	iGM RESINS	16.40
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Sudarshan	5.45
Corrosion inhibitor	HEUCORIN® RZ	Sudarshan	0.60
Magnesium silicate	Microtalc™ IT Extra	Elementis	22.35
Photoinitiator	Omnirad 2022	iGM RESINS	1.95
Grind.			

---



---

 100.00

Gf-SC05\_001-01\_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.