

in Powder coating

Specialty coatings

Sudarshan formulation No. 590-05

Rev. Number: 01.01

11/10

Function	Product	Producer	PBW
Polyester resin	Uralac® P 885	DSM Coating Resins	65.30
Crosslinker	Primid® XL-552	EMS-CHEMIE	3.45
Anticorrosive pigment	HEUCOSIL™ CTF	Sudarshan	5.00
Nickel antimony titanium yellow	HEUCODUR® Yellow 152	Sudarshan	0.06
Chrome antimony titanium buff	HEUCODUR® Yellow 252	Sudarshan	0.02
Carbon black pigment	Colour Black FW 200	Orion Engineered Carbons	0.02
Titanium dioxide	KRONOS® 2310	KRONOS	8.35
Barium sulfate	BLANC FIXE™ F	Venator	15.80
Degassing agent	Ceridust® 9615 A	Clariant	1.00
Flow control agent	Resiflow® PV-88	Estron Chemical	1.00
Add.			

100.00

Gf-SC06_006-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.