

# HEUCOPHOS® ZAM-PLUS / HEUCORIN® RZ / HEUCOFLASH™ LQ2

in Alkyd emulsion



Water based coatings

Sudarshan formulation No. 972-07

Rev. Number: 01.02

09/23

Function	Product	Producer	PBW
	Demi. water		8.00
Wetting and dispersing agent	DISPERBYK®-190	BYK-Chemie	1.00
Rheology modifier	Rheovis®PE 1320 NC/PU 1214 NC, 1:0.3	BASF	0.60
Defoamer/Deaerator	TEGO® Airex 902 W	Evonik	0.20
<b>Premix.</b>			
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Sudarshan	6.10
Corrosion inhibitor	HEUCORIN® RZ	Sudarshan	0.65
Magnesium silicate	MISTRON® 75-6 A	Imerys	4.10
Calcium/Magnesium carbonate	MICRODOL® SUPER	Omya	10.60
Carbon black pigment	Lamp black® 101	Orion Engineered Carbons	0.05
Titanium dioxide	KRONOS® 2190	KRONOS	10.30
<b>Grind with a bead mill.</b>			
	Demi. water		3.00
PU modified alkyd emulsion	WorléeSol E 330 W	Worlée-Chemie	49.50
	Demi. water		3.80
Defoamer/Deaerator	TEGO® Airex 902 W	Evonik	0.30
Solvent	Butyl glycol		0.50
Flash rust inhibitor	HEUCOFLASH™ LQ2	Sudarshan	1.00
Rheology modifier	Rheovis®PE 1320 NC/PU 1214 NC, 1:0.3	BASF	0.30
<b>Add while stirring.</b>			
			100.00
<b>Adjust pH 7.0 - 8.5 with ammonia.</b>			
<b>Specifications</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			20.0
PVC in %			34.6
PVC / CPVC			0.6
Solids in %			52.7

Gf-WB01\_021-01\_02A

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.