

in 2K Epoxy

Water based coatings

Sudarshan formulation No. 882-02

Rev. Number: 01.01

10/18

Function	Product	Producer	PBW
Component A			
Epoxy dispersion	BECKOPOX® EP 387w/52WA	Allnex	48.15
	Demi. water		6.10
Defoamer	ADDITOL® VXW 6393	Allnex	0.20
Wetting and dispersing agent	ADDITOL® VXW 6208/60	Allnex	2.05
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPA	Sudarshan	3.95
Iron oxide yellow pigment	BAYFERROX® 3920	LANXESS	0.40
Titanium dioxide	KRONOS® 2190	KRONOS	14.35
Barium sulfate	EWO	Sachtleben Minerals	12.30
Iron oxide black pigment	BAYFERROX® 306	LANXESS	0.80
Grind with a bead mill.			
Coalescing agent	Eastman Texanol™	Eastman Chemical	0.45
Defoamer	ADDITOL® VXW 6393	Allnex	0.20
Levelling and wetting agent	ADDITOL® VXW 6503 N	Allnex	0.20
Rheology modifier	ADDITOL® VXW 6388	Allnex	0.35
Add while stirring.			
			89.50
Component B			
Curing agent	BECKOPOX® EH 613w/80WA	Allnex	5.25
	Demi. water		5.25
Premix and add while stirring.			
			10.50
Mix components A and B thoroughly prior to use.			
			100.00

Specifications		
Vol.-% Anticorrosive pigment reg. pigment/filler		17.7
PVC in %		24.2
PVC / CPVC		0.4
Solids in %		62.9
Crosslinking in %		75.0

Gf-WB02_023-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.