

in Silicone resin

Water based coatings

Sudarshan formulation No. 519-06

Rev. Number: 01.01

06/10

Function	Product	Producer	PBW
	Demi. water		11.85
Solvent	Butyl glycol		1.00
Wetting and dispersing agent	TEGO® Dispers 755 W	Evonik	2.95
Defoamer	TEGO® Foamex K 3	Evonik	0.80
Rheology modifier	AEROSIL® R 972	Evonik	1.00
Premix.			
Anticorrosive pigment	HEUCOPHOS® SAPP	Sudarshan	3.95
Magnesium silicate	Microtalc™ IT Extra	Elementis	7.75
Iron and manganese oxide black	BAYFERROX® 303 T	LANXESS	12.85
Carbon black pigment	PRINTEX® L	Orion Engineered Carbons	1.25
Grind.			
Methyl phenyl silicone resin	SILIKOPHEN® P40/W	Evonik	56.60
Add while stirring.			

 100.00
Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	18.1
PVC in %	22.9
CPVC in %	45.7
PVC / CPVC	0.5

Gf-WB05_002-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.