

in Silicone resin

Water based coatings

Evonik Tego formulation No. P40W 9 002

Rev. Number: 01.01

10/20

Function	Product	Producer	PBW
	Demi. water		20.30
Wetting and dispersing agent	TEGO® Dispers 750 W	Evonik	1.50
Defoamer	Mineral oil defoamer		0.20
Premix.			
Anticorrosive pigment	HEUCOSIL™ CTF	Sudarshan	5.00
Muscovite mica	MICA TM	Aspanger	14.00
Copper chromite black spinel	HEUCODUR® Black 9-100	Sudarshan	8.00
Grind.			
Methyl phenyl silicone resin	SILIKOPHEN® P40/W	Evonik	45.00
	Demi. water		6.00
Add while stirring.			

100.00

Specifications	
Vol.-% Anticorrosive pigment reg. pigment/filler	26.0
PVC in %	32.2
Solids in %	50.0

Gf-WB05_003-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.