

in Vinyl acrylic dispersion

Water based coatings

DSM Coating Resins formulation No. WB-6039

Rev. Number: 01.01

07/98

Function	Product	Producer	PBW
	Demi. water		14.00
Rheology modifier	Natrosol™ 250 HBR	Ashland	0.10
Premix.			
Defoamer	Foamaster® S	BASF	0.30
Dispersing agent	BYK®-155/35	BYK-Chemie	0.30
Plasticizer	Pycal™ 94	Croda	2.30
Magnesium silicate	MISTRON® MONOMIX G	Imerys	18.10
Anticorrosive pigment	HEUCOPHOS® ZPA	Sudarshan	4.20
Iron oxide red pigment	Copperas Red® Iron Oxide R4098	Venator	2.80
Grind to a fineness of app. 30 microns, temperature < 40 °C.			
	Demi. water		1.60
Rheology modifier	ACRYSOL™ RM-2020	Dow	0.80
Substrate wetting agent	SURFYNOL® 104 H	Evonik	0.30
Vinyl acrylic dispersion	Haloflex™ 202-S	DSM Coating Resins	55.20
Add while stirring.			
			100.00

Specifications	
PVC in %	26.4
Solids in %	60.9

Gf-WB06_004-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.