

in Styrene acrylic dispersion

Water based coatings

Sudarshan formulation No. 03252

Rev. Number: 01.01

05/03

Function	Product	Producer	PBW
Styrene acrylic dispersion	NeoCryl® XK-85	DSM Coating Resins	11.75
	Demi. water		2.90
Defoamer	Drewplus™ TS-4380	Ashland	0.05
Wetting and dispersing agent	NUOSPERSE® W-22	Elementis	1.35
Rheology modifier	Borchi® Gel L 75 N, 50% in demi. water	Borchers	0.85
Corrosion inhibitor	NALZIN® FA 179	Elementis	0.55
Solvent	Butyl glycol		1.75
Styrene acrylic dispersion	NeoCryl® A-1094	DSM Coating Resins	2.35
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Sudarshan	8.65
Corrosion inhibitor	HEUCORIN® RZ	Sudarshan	0.95
Magnesium silicate	FINNTALC M10	Elementis	8.15
Titanium dioxide	KRONOS® 2190	KRONOS	7.70
Carbon black pigm. preparation	Hostatint® Black GR 30	Clariant	0.95
Grind to a fineness of app. 20 microns.			
Styrene acrylic dispersion	NeoCryl® XK-85	DSM Coating Resins	47.00
Solvent	Butyl glycol		2.65
Coalescing agent	Eastman Texanol™	Eastman Chemical	1.20
Defoamer	FoamStar® SI 2213	BASF	1.20
Add grind while stirring.			
			100.00
Adjust pH 9.0 with ammonia, 25%.			
Specifications			
PVC in %			26.6
Solids in %			52.8

Gf-WB06_011-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.