

## in Vinyl acrylic dispersion

Water based coatings

Sudarshan formulation No. 390-11

Rev. Number: 01.01

05/08

Function	Product	Producer	PBW
	Demi. water		16.50
Solvent	Butyl glycol		1.90
Rheology modifier	BENTONE® LT	Elementis	0.15
Defoamer	Foamaster® H 2	BASF	0.20
Surfactant	Synperonic™ PE/F87	Croda	1.00
	Demi. water		2.45
Substrate wetting agent	SURFYNOL® 104 E	Evonik	0.30
Preservative	Acticide® MBS	Thor	0.05
Dispersing agent	BYK®-155	BYK-Chemie	0.50
<b>Premix.</b>			
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Sudarshan	6.60
Corrosion inhibitor	HEUCORIN® RZ	Sudarshan	0.75
Talc/chlorite filler	LUZENAC 20M0	Imerys	20.70
Carbon black pigm. preparation	MONOLITE® Black XBE-HD Paste	Sudarshan	3.30
Grind to a fineness of < 25 microns, temperature < 40 °C.			
Vinyl acrylic dispersion	Haloflex™ 202	DSM Coating Resins	44.20
Adjust pH 4.0 with ammonia, 25% prior to addition.			
Flash rust inhibitor	CHE®-COAT-CI L8AF	C.H. Erbslöh	0.20
Flash rust inhibitor	CHE®-COAT-CI L8NF	C.H. Erbslöh	0.20
Coalescing agent	Eastman Texanol™	Eastman Chemical	1.00
Add while stirring.			
			100.00

**Specifications**

Vol.-% Anticorrosive pigment reg. pigment/filler	19.7
PVC in %	36.4
CPVC in %	45.5
PVC / CPVC	0.8

Gf-WB06\_023-01\_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.