

in Styrene acrylic ester dispersion

Water based coatings

Sudarshan formulation No. 09312

Rev. Number: 01.01

04/09

Function	Product	Producer	PBW
Styrene acrylic ester dispersion	REVACRYL® AE 6030	Synthomer	55.40
Defoamer	CHE®-COAT-DF 681 F	C.H. Erbslöh	0.30
Solvent	Butyl glycol		4.00
Surfactant	Lutensit® A-EP	BASF	0.30
Premix. Adjust pH 9.0 with ammonia, 25%.			
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Sudarshan	12.00
Calcium carbonate	Millicarb®	Omya	6.00
Magnesium silicate	MISTRON® 754 G	Imerys	4.00
Iron oxide red pigment	BAYFERROX® 222 FM	LANXESS	15.00
Rheology modifier	RHEOLATE® FX 1010, 10% demi. water	Elementis	1.10
Grind with a bead mill.			
Defoamer	CHE®-COAT-DF 681 F	C.H. Erbslöh	0.40
Flash rust inhibitor	CHE®-COAT-CI L8AF	C.H. Erbslöh	0.25
Flash rust inhibitor	CHE®-COAT-CI L8NF	C.H. Erbslöh	0.25
Solvent	White Spirit		1.00
Add to the grind.			
			100.00
Adjust pH 9.0 with ammonia, 25%.			
Specifications			
Vol.-% Anticorrosive pigment reg. pigment/filler			34.0
PVC in %			29.0
Solids in %			66.1

Gf-WB06_027-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.