

in Butyl styrene acrylic dispersion

Water based coatings

Sudarshan formulation No. 567-17

Rev. Number: 01.01

03/10

Function	Product	Producer	PBW
Butyl styrene acrylic dispersion	Acronal® LR 8977	BASF	48.65
Defoamer	BYK®-022	BYK-Chemie	0.25
Substrate wetting agent	SURFYNOL® 104 PA	Evonik	0.40
Premix.			
	Demi. water		7.10
Surfactant	Lutensit® A-EP	BASF	0.10
Neutralizing agent	Ammonia		0.30
Premix and add while stirring.			
Solvent	Solvenon® PP	BASF	0.75
Solvent	Exxsol™ D60	ExxonMobil	0.75
Solvent	Butyl glycol		0.75
Add while stirring.			
Anticorrosive pigment	HEUCOPHOS® ZMP	Sudarshan	11.85
Corrosion inhibitor	HEUCORIN® RZ	Sudarshan	1.30
Talc/chlorite filler	LUZENAC 20M2	Imerys	14.85
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	11.00
Grind with a bead mill.			
Defoamer	BYK®-022	BYK-Chemie	0.15
Add while stirring.			
Flash rust inhibitor	CHE®-COAT-CI LNFA4	C.H. Erbslöh	0.55
	Demi. water		0.55
Premix and add while stirring. Adjust pH 9.0 - 9.5 with ammonia.			
Rheology modifier	Rheovis® PU 1280	BASF	0.35
Solvent	Butyl glycol		0.35
Premix and add while stirring.			
			100.00
Specifications			
Vol.-% Anticorrosive pigment reg. pigment/filler			26.6
PVC in %			33.1
PVC / CPVC			0.6

Gf-WB06_031-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.