

in Styrene acrylic dispersion

Water based coatings

Sudarshan formulation No. 955-04

Rev. Number: 01.01

11/19

Function	Product	Producer	PBW
Styrene acrylic dispersion	Acronal® PRO 7600	BASF	40.55
Defoamer	FoamStar® SI 2210	BASF	0.20
	Demi. water		5.85
Dispersing agent	Hydropalat® WE 3425	BASF	0.05
Neutralizing agent	Ammonia, 25%		0.55
Premix.			
Coalescing agent	DOWANOL™ PPh	Dow	0.70
Solvent	Exxsol™ D60	ExxonMobil	0.70
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZMP	Sudarshan	7.75
Magnesium silicate	Talc LP30	LITHOS Industrial Minerals	3.40
Zinc sulfide/Barium sulfate	Lithopone 30% L	Venator	12.15
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	8.10
Grind with a bead mill.			
Styrene acrylic dispersion	Acronal® PRO 7600	BASF	17.15
Defoamer	FoamStar® SI 2210	BASF	0.20
Add to the grind.			
Flash rust inhibitor	CHE®-COAT-CI LNFA4	C.H. Erbslöh	0.20
	Demi. water		0.20
Premix and add while stirring.			
Rheology modifier	Rheovis® PU 1280	BASF	0.40
Solvent	Butyl glycol		1.30
Premix and add while stirring.			
Neutralizing agent	Ammonia, 25%		0.55
Add to the grind.			
			100.00
Adjust pH 9.3 - 9.5 with ammonia, 25%.			
Specifications			
Vol.-% Anticorrosive pigment reg. pigment/filler			28.0
PVC in %			23.3
PVC / CPVC			0.4
Solids in %			60.3

Gf-WB06_053-01_01B

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.