

Full Shade Ca/Zn compound; 5% pigmentation
Product Description

Dry preparation of inorganic and/or organic pigments with unstabilized PVC.

Appearance	Black powder
------------	--------------

Technical Data

	Unit	Value	Test Method
Volatile matter (105 °C)	[%]	<1.0	
Density	[g/cm ³]	typ. 1.3	acc. to ISO 787-10
Bulk density	[g/cm ³]	typ. 0.6	acc. to ISO 697
PVC K-value		typ. 58	

PVC K-value is based on information from PVC supplier.

Fastness Properties
Resistance to Chemicals

	Value	Test Method
Acid	5	rating acc. to DIN EN ISO 105-A03
Alkali	5	rating acc. to DIN EN ISO 105-A03

Acid/alkali resistance: Product was dipped into hydrochloric acid (10%) or soda solution (10%). Rating with gray scale: 1=poor, 5=excellent.

	Value	Test Method
Migration	5	rating acc. to DIN EN ISO 105-A03
Heat resistance [°C]	220	
Light fastness [full shade]	7 - 8	rating acc. to DIN EN ISO 105-B02

Migration, heat resistance and light fastness are based on information from raw material supplier.

The weather fastness of a colored rigid PVC is influenced by many factors especially the stabilization of the PVC-compound. Hence the weathering has to be tested in the polymer system of the user.

Packaging and Handling

Packaging	25 kg paper bags
Packaging	Different types of packaging are available on request

Tds-hp_99023se-01_02

Disclaimer - The information given in this data sheet is based on the present state of our knowledge & is intended as a general description of our products & their possible applications. Neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Because of the multitude of formulations, production & application conditions, all the above mentioned data have to be adjusted to the circumstances of the processor. As customer use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in any particular application. In addition to that, the legal rights of third parties must always be considered. No liabilities, including those for patent rights, can be derived from this fact for individual cases. It cannot be ruled out that this product contains particles < 0.1 µm. Any user of this product is responsible for determining the suitability of Sudarshan's products for its particular application & to ensure that any proprietary rights & existing laws & legislation are observed.